

Thermal Soft Touch 30 Micron

- Bi-axially Oriented Polypropylene Film (BOPP)
- SOFT TOUCH finish
- Exclusive peach skin texture
- Enhances original colours of your print
- Outstanding surface adhesion for all types of coatings, inks, hot-melt and foils
- Superior bonding strength
- Low melt thermal adhesive

Ever versatile and useable; this extensive range of Bi-axially Oriented Polypropylene Films (BOPP) include Corona pre-treated / coated and print receptive grades neatly paired with user friendly low-melt thermally activated adhesive.

Used daily by our customers on a range of products including luxury packaging, brochures, catalogues, book covers and jackets, labels and posters.

Specifications

BASE FILM	Polypropylene Film (BOPP)
SURFACE FINISH	Matt/Velvet
AVAILABLE STOCK WIDTHS	315, 440, 445, 450, 510, 610, 630, 635, 710, 890, 1010

Other widths available upon request

Typical Properties

PROPERTY		UNIT	TEST METHOD	VALUE
THICKNESS		(μm)		30
YIELD		m^2/kg In^2/Lb	Internal Test Method	37.45 26 333
WETTING TENSION	B	Dynes/cm	ASTM D 2578	≥ 46
C.O.F FILM/FILM	B/B		ASTM D1894	0.75
APPLICATION TEMPERATURE	A	$^{\circ}\text{C}$ $^{\circ}\text{F}$	Internal Test Method	110 – 120 230 – 250
LAMINATION STRENGTH	A	$\text{N}25.4/\text{mm}$ Lb/In	Internal Test method	≥ 7.5 ≥ 1.68
GLOSS	B	%	ASTM D 2457 45 $^{\circ}$	6

A: Adhesive Side B: Soft Touch Side

The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.



01844 208308 info@gifproducts.co.uk www.gifproducts.co.uk

Graphic Image Films Ltd. Unit 5 Ridge Way • Crendon Industrial Park • Long Crendon • Buckinghamshire • HP18 9BF